

Dorval, October 05, 2016

Mr. Louis-André Gaudreau  
DiZal Inc.  
4000 rue Jean-Marchand, Local 108  
Québec, Qc G2C 1Y6  
CANADA

---

**TEST REPORT # MI-16-8955-2e**

---

On March 27<sup>th</sup>, Micom Laboratories Inc. received Aluminum samples to perform Surface Finish Testing.

**SAMPLE DESCRIPTION:**

- Sample: DiZal Inc. CIZAL 15/03/16



*Sample: DiZal*

---

This report shall not be reproduced except in full, without the written approval of the laboratory. The results herein relate only to the items tested.

**REFERENCE TEST METHOD:**

ASTM D6578 (Determination of Graffiti Resistance)

**RESULTS:**

Tests performed between 2016-05-20 and 2016-08-26.

- **ASTM D6578** (Determination of Graffiti Resistance)

Cleaning Agent	Description
6.5.1	Dry, Lint-Free cotton cloth
6.5.2	Mild Detergent
6.5.3	Isopropyl Alcohol
6.5.4	Mineral Spirits
6.5.5	Xylene
6.5.6	Methyl Ethyl Ketone

Material	Description	Cleanability rating
		DiZal
6.3.1	Solvent-Based Permanent Marker, blue	<b>8</b>
6.3.2	Solvent-Based Acrylic Spray Paint, red	<b>7</b>
6.3.3	Solvent-Based Alkyd Spray Paint, red	<b>7</b>
6.3.4	Wax Pen, blue or black	<b>9</b>
6.3.5	Ballpoint Ink	<b>8</b>
6.3.6	Water-Based Ink Marker, black	<b>6</b>

This report shall not be reproduced except in full, without the written approval of the laboratory. The results herein relate only to the items tested.

Rating

- 10 = Cleanable with a dry rag
- 9 = Cleanable with Detergent
- 8 = Cleanable with Isopropyl Alcohol
- 7 = Cleanable with Mineral Spirits
- 6 = Cleanable with Xylene
- 5 = Cleanable with Methyl Ethyl Ketone
- 4 = Not Cleanable, Gloss loss
- 3 = Not Cleanable, Slight shadow
- 2 = Not Cleanable, Heavy shadow
- 1 = Not Cleanable, shadow and gloss loss



*Sample: DiZal after graffiti test*

Prepared by:

Approved by:

\_\_\_\_\_  
Adrien Mulot  
Technician

\_\_\_\_\_  
David Rousseau, M. Sc.  
Lab Manager

This report shall not be reproduced except in full, without the written approval of the laboratory. The results herein relate only to the items tested.